



# Thermostop

## Technical Data

Thermostop at 3 / 5 / 6 / 10 mm

<b>Thermal conductivity</b>	0,08 - 0,09 W/mK	DIN EN 12664
<b>Density</b>	> 0,70 g/cm <sup>3</sup>	DIN EN ISO 1183
<b>Compressive strength</b>	> 10 N/mm <sup>2</sup>	DIN 53421 (following) DIN EN ISO 844
<b>Impact strength</b>	> 13 KJ/m <sup>2</sup>	DIN 53457
<b>Compressive stress</b> (at 30% compression)	> 16 N/mm <sup>2</sup>	DIN 53421 (following) DIN EN ISO 844
<b>Elastic module</b>	> 1000 N/mm <sup>2</sup>	DIN EN ISO 178
<b>Vicat A</b>	76 °C	DIN EN ISO 306
<b>Fire classification</b>	B1	DIN 4102
<b>Water absorption</b>	< 1 %	DIN EN ISO 62

These values are guideline limits at average bulk density. Small deviations may occur depending upon thickness. The indications presented in this technical information sheet are based on the information provided by the manufacturer of the material. No guarantee can be made concerning the validity thereof or results derived therefrom. Subject to modifications.

Status 10/2021